

## LAMCO HPL STANDARD (HGS-HGF)

Material consisting of layers of kraft paper impregnated with thermosetting resins and a surface layer of decorative paper impregnated with aminoplastic resins, all bonded together by means of high pressure (9 Mpa) and high temperature (150°C). It is also available in flame retardant version, where fire retardant additives are mixed to phenolic resins. This material is produced in conformity to EN 438-3:2005.

PROPERTY	TEST METHOD (EN 438: 2005)	PROPERTY OR ATTRIBUTE	UNIT	VALUES HGS-HGF
<b>Thickness ± tolerance</b>	EN 438-2.5	thickness (t)	mm	0,5 t 1,0 ±0,10 1,0 < t < 2,0 ±0,15
<b>Flatness</b>	EN 438-2.9	maximum deviation	mm/mtl	60
<b>Resistance to surface wear</b>	EN 438-2.10	wear resistance	revs	IP ≥ 150 A ≥ 350
<b>Resistance to immersion in boiling water</b>	EN 438-2.12	appearance gloss finish appearance other finishes	rating	≥ 3 4
<b>Resistance to dry heat (180°C)</b>	EN 438-2.16	appearance gloss finish appearance other finishes	rating	≥ 3 ≥ 4
<b>Resistance to wet heat (100°C)</b>	EN 12721	appearance gloss finish appearance other finishes	rating	≥ 3 ≥ 4
<b>Dimensional stability at elevated temperature</b>	EN 438-2.17	cumulative dimensional change	% long. % transv.	≤ 0,55 ≤ 1,05
<b>Resistance to impact by small diameter ball</b>	EN 438-2.20	spring force	N	≥ 20
<b>Resistance to cracking</b>	EN 438-2.23	appearance	rating	≥ 4
<b>Resistance to scratching<sup>(1)</sup></b>	EN 438-2.25	force	rating	3
<b>Resistance to staining</b>	EN 438-2.26	app. groups 1-2 appear. groups 3	rating	5 ≥ 4
<b>Lightfastness</b>	EN 438-2.27	contrast	grey scale rating	≥ 4
<b>Resistance to cigarette burns</b>	EN 438-2.30	appearance	rating	≥ 3
<b>Resistance to water vapour</b>	EN 438-2.14	appearance gloss finish appearance other finishes	rating	≥ 3 ≥ 4
<b>Electrical resistance</b>	EN 61340-4-1	R <sub>v</sub> (23°C /50% RH)	Ohm	10 <sup>9</sup> - 10 <sup>11</sup>
<b>Density</b>	ISO 1183	density	gr/cm <sup>3</sup>	≥ 1,40

(1) Resistance to scratching is depending from finish and colour.

Note: The colour of individual lots may vary as a result of the technology and tyte of pigment used. Pay attention to the direction of the texture.

## LAMCO HPL STANDARD (HGS-HGF)

### FIRE PERFORMANCE

TEST METHOD	STANDARD	CLASSIFICATION	
		HGF	HGS
Small flame and radiant panel	UNI 8457 UNI 9174 UNI 9177	class 1	class 1
Spread of flame	BS 476-7	class 1	class 2
Brandschacht	DIN4102-1	B1	B2
Epiradiateur	NF P 92-501	M1	min. M3
Smoke density and toxicity	NF F 16-101	min F2	min F2
Heat release	IMO Res. A 653(16)	pass	pass

Note: Fire test performance will depend on laminate thickness and construction, substrate type and thickness, and adhesive used.